

## DESCRIPTION:

**ELASTOBOND PMB** is aliphatic polyurethane modified rubberised elastomeric waterproofing membrane .

## PROPERTIES:

- Highly elastic and forms rubberised membrane
- Single component
- High adhesive strength
- Superior tensile strength
- Highly resistant UV radiations
- Water base, no mixing required

## APPLICATION PROCEDURE

First dilute ELASTOBOND PMB with water in ratio of 1 part pmb : 2 part water as a priming coat

Then apply first coat of ELASTOBOND PMB by brush on priming coat

After 4 hrs apply second coat of ELASTOBOND PMB

**DO NOT DILUTE FIRST COAT AND SECOND COAT OF ELASTOBOND PMB** to achieve desired thickness And crack bridging property

**Coverage** : 10 sqft per kg for two coats for 1 mm thickness

**Packing** : 10 kg and 20 kg plastic container

## USES :

- Sunken portion of toilet and bathrooms
- Asbestos sheet
- Concrete roof
- Basement and retaining wall plinth protection

## TECHNICAL DATA

Colour	: black
Base	: aliphatic polyurethane modified bitumen emulsion coating
Solid content	: 55%
Elongation at break	: 1000%
Tensile strength	: 1.5 N/MM2
Crack bridging ability	: 2 mm



Disclaimer: The information given in good faith is based on our in-house testing & site results. However, we do not guarantee the same as the conditions of actual use are beyond our control.

**WE HAVE OUR OWN PROJECT DIVISION & UNDERTAKE LARGE PROJECTS.**